



Product Name : **S-Corit TR**

Maximum Service Temperature ° C **1360**

Apparent Density g/cm³ **1,9**

Apparent Porosity % **24**

Modulus of Rupture 3-Point Test

at 20 °C	N/mm ²	9
at 1000 °C	N/mm ²	-
at 1100 °C	N/mm ²	-
at 1200 °C	N/mm ²	-
at 1250 °C	N/mm ²	-
at 1300 °C	N/mm ²	-

Thermal Expansion at 1000 °C 10⁻⁶. K⁻¹ **2**

Thermal Conductivity W .m⁻¹.K⁻¹ **1,0**

Specific Heat Coefficient at 20 °C J.kg⁻¹. K⁻¹ **900**

Chemical Composition:

Al ₂ O ₃	%	39
SiO ₂	%	50
MgO	%	8

All these data are given for information only and can be under no circumstances considered as specifications. The customer must validate under its own responsibility the behaviour and performances of the product in its own process before use