



Product Name :	<b>Aptakorit CME</b>		
----------------	----------------------	--	--

Maximum Service Temperature	°C	<b>1350</b>	
-----------------------------	----	-------------	--

Apparent Density	g/cm <sup>3</sup>		
------------------	-------------------	--	--

Apparent Porosity	%		
-------------------	---	--	--

Modulus of Rupture 3-Point Test			
	at 20 °C	N/mm <sup>2</sup>	
	at 1000 °C	N/mm <sup>2</sup>	
	at 1100 °C	N/mm <sup>2</sup>	
	at 1200 °C	N/mm <sup>2</sup>	
	at 1250 °C	N/mm <sup>2</sup>	
	at 1300 °C	N/mm <sup>2</sup>	

Thermal Expansion	at 1000 °C	x 10 <sup>-6</sup> K <sup>-1</sup>	<b>2,1</b>
-------------------	------------	------------------------------------	------------

Thermal Conductivity		W m <sup>-1</sup> K <sup>-1</sup>	<b>1,0</b>
----------------------	--	-----------------------------------	------------

Specific Heat Coefficient	at 20 °C	J/kg K	<b>0,9</b>
---------------------------	----------	--------	------------

Softening under Load	To	°C	<b>1384</b>
----------------------	----	----	-------------

Chemical Composition :			
	Al <sub>2</sub> O <sub>3</sub>	%	<b>38,8</b>
	SiO <sub>2</sub>	%	
	MgO	%	<b>7,6</b>

These data are for information only. They correspond to the values commonly observed for the materials produced.