



Product Name :	Aptakorit HT		
----------------	---------------------	--	--

Maximum Service Temperature	°C	1300	
-----------------------------	----	-------------	--

Apparent Density	g/cm ³	1,97	
------------------	-------------------	-------------	--

Apparent Porosity	%	28,8	
-------------------	---	-------------	--

Modulus of Rupture 3-Point Test			
at 20 °C	N/mm ²	18,2	
at 1000 °C	N/mm ²	-	
at 1100 °C	N/mm ²	25,8	
at 1200 °C	N/mm ²	21,3	
at 1250 °C	N/mm ²	18,1	
at 1300 °C	N/mm ²	-	

Thermal Expansion	at 1000 °C	x 10 ⁻⁶ K ⁻¹	3,7
-------------------	------------	------------------------------------	------------

Thermal Conductivity	W m ⁻¹ K ⁻¹	1,0	
----------------------	-----------------------------------	------------	--

Specific Heat Coefficient	at 20 °C	J/kg K	0,9
---------------------------	----------	--------	------------

Softening under Load	To	°C	1388
----------------------	----	----	-------------

Chemical Composition :			
	Al ₂ O ₃	%	48,1
	SiO ₂	%	
	MgO	%	4,0

These data are for information only. They correspond to the values commonly observed for the materials produced.