



Product Name :	Aptakorit ZSA		
----------------	----------------------	--	--

Maximum Service Temperature	°C	1300	
-----------------------------	----	-------------	--

Apparent Density	g/cm ³	1,92	
------------------	-------------------	-------------	--

Apparent Porosity	%	25,7	
-------------------	---	-------------	--

Modulus of Rupture 3-Point Test			
	at 20 °C	N/mm ²	24,8
	at 1000 °C	N/mm ²	-
	at 1100 °C	N/mm ²	25,1
	at 1200 °C	N/mm ²	18,2
	at 1250 °C	N/mm ²	15,5
	at 1300 °C	N/mm ²	

Thermal Expansion	at 1000 °C	x 10 ⁻⁶ K ⁻¹	2,7
-------------------	------------	------------------------------------	------------

Thermal Conductivity		W m ⁻¹ K ⁻¹	1,0
----------------------	--	-----------------------------------	------------

Specific Heat Coefficient	at 20 °C	J/kg K	0,9
---------------------------	----------	--------	------------

Softening under Load	To	°C	1377
----------------------	----	----	-------------

Chemical Composition :			
	Al ₂ O ₃	%	37,9
	SiO ₂	%	
	MgO	%	8,6

These data are for information only. They correspond to the values commonly observed for the materials produced.