



Product Name :	SC 90GB		
----------------	----------------	--	--

Maximum Service Temperature	°C	1350	
-----------------------------	----	-------------	--

Apparent Density	g/cm ³	2,90	
------------------	-------------------	-------------	--

Apparent Porosity	%	< 1,0	
-------------------	---	-----------------	--

Modulus of Rupture 4-Point Test			
	at 20 °C	N/mm ²	220
	at 1300 °C	N/mm ²	275

Modulus of Elasticity	GPa		
-----------------------	-----	--	--

Thermal Expansion	at 1000 °C	x 10 ⁻⁶ K ⁻¹	4,0
-------------------	------------	------------------------------------	------------

Thermal Conductivity	at 200 °C	W m ⁻¹ K ⁻¹	130
	at 1200 °C	W m ⁻¹ K ⁻¹	35

Chemical Composition :			
	SiC content	%	78
	free Si content	%	22

These data are for information only. They correspond to the values commonly observed for the materials produced.

First publication: 2007 - 02 - 17	Updating: 2007 - 02 - 17
-----------------------------------	--------------------------