



Product Name :

Aptazirox CF

Maximum Service Temperature

oxidising atmosphere	° C	1350
protective atmosphere	° C	

Apparent Density	g/cm ³	4,10
------------------	-------------------	-------------

Apparent Porosity	%	26,8
-------------------	---	-------------

Modulus of Rupture 3-Point Test

at 20 °C	N/mm ²	39,6
at 1300 °C	N/mm ²	

Thermal Expansion	at 1000 °C x 10 ⁻⁶ K ⁻¹	8,50
-------------------	---	-------------

Chemical Composition :

CaO	%	4,00
ZrO ₂	%	95,0

All data are typical values, determined on test specimens. They are subject to reasonable variations in the common production process.

First publication: 16-05-2008.	Updating: 30-07-2009.
--------------------------------	-----------------------